

**Amendments to the Claims:**

The following Listing of Claims will replace all prior versions, and listings, of claims in the application:

**Listing of Claims**

1. (Cancelled)
2. (Previously Presented) A composition according to claim 24, further comprising an organic solvent.
3. (Previously Presented) A composition according to claim 2, wherein said organic solvent comprises a solvent capable of dissolving between 0.01% and 5.0% by weight of component (a).
4. (Original) A composition according to claim 2, wherein said organic solvent is an alcohol, ketone, ether or ester.
5. (Cancelled)
6. (Previously Presented) A composition according to claim 24, wherein  $R_f$  in Formula (I) is of the formula:
 
$$-((R_f^3)_q-R_f^2-O)_z-R_f^1-(O-R_f^2-(R_f^3)_q)- \quad (III)$$
 wherein  $R_f^1$  is a perfluorinated alkyl or a perfluorinated alkylene group,  $R_f^2$  is a perfluorinated polyalkyleneoxy group consisting of perfluorinated alkyleneoxy groups having 1, 2, 3 or 4 carbon atoms or a mixture of such perfluorinated alkyleneoxy groups;  $R_f^3$  is a perfluorinated alkylene group or a substituted perfluorinated alkyl group; q and q' are independently chosen from 0 or 1; z is from 4 to 30, and z' is 0 to 30.
7. (Previously Presented) A composition according to claim 6, wherein  $R_f^2$  comprises repeating units selected from the group consisting of  $-(C_nF_{2n}O)-$ ,  $-(CF(Z)O)-$ ,  $-(C_nF_{2n}CF(Z)O)-$ , and  $-(CF_2CF(Z)O)-$ , and combinations thereof, wherein n is at least 1 and wherein Z is a fluorine

atom, a perfluoroalkyl group, a substituted perfluoroalkyl group, an oxygen-substituted perfluoroalkyl group, a perfluoroalkoxy group, or an oxygen-substituted perfluoroalkoxy group.

8. (Previously Presented) A composition according to claim 6, wherein  $R_f^3$  comprises repeating units selected from the group consisting of  $-(C_nF_{2n})-$  and  $-(CF(Z))-$ , and combinations thereof, wherein n is at least 1 and wherein Z is a fluorine atom, a perfluoroalkyl group, a substituted perfluoroalkyl group, an oxygen-substituted perfluoroalkyl group, a perfluoroalkoxy group, or an oxygen-substituted perfluoroalkoxy group.

9. (Previously Presented) A composition according to claim 24, wherein  $R_f$  is  $-CF_2O(CF_2O)_m(C_2F_4O)_pCF_2-$ ,  $-CF_2O(C_2F_4O)_pCF_2-$ ,  $-CF(CF_3)(OCF_2(CF_3)CF)_pO(CF_2)_mO(CF(CF_3)CF_2O)_pCF(CF_3)-$ , or combinations thereof, where an average value for m and p is 0 to 50 and m and p are not each independently 0.

10. (Previously Presented) A composition according to claim 24 wherein  $R_f$  is  $CF_3CF_2O(CF_2O)_m(C_2F_4O)_pCF_2-$ ,  $CF_3CF_2CF_2O(CF(CF_3)CF_2O)_pCF(CF_3)-$ ,  $CF_3CF_2O(C_2F_4O)_pCF_2-$ ,  $CF_3CF(CF_3)O-(CF(CF_3)CF_2O)_pCF(CF_3)-$ , or combinations thereof, where an average value for m and p is 0 to 50 and m and p are not each independently 0.

11. – 17. (Cancelled)

18. (Previously Presented) A composition according to claim 24, wherein component (a) is present in an amount of between 1 wt-% and 50 wt-%; component (b) is present in an amount between 50 wt-% and 99 wt-%; and component (c) is present in an amount between 0 wt-% and 20 wt-%, the weight-% being based on the total weight of the components.

19. (Previously Presented) The composition according to claim 24, wherein said composition is derivable from a partial condensation reaction of components (a), (b) and (c).

20. (Previously Presented) The composition according to claim 4, wherein said composition is derivable from a complete condensation reaction of components (a), (b) and (c).


21. (Previously Presented) A process for preparing a partial or complete condensate comprising reacting components (a), (b) and (c) according to claim 24 in a polar organic solvent in the presence of water and an acid or base catalyst.

22. (Previously Presented) A method of treating a substrate comprising applying to at least part of a surface of said substrate a composition according to claim 24.

23. (Original) A coated substrate as prepared by the method according to claim 21.

24. (Currently Amended) A composition comprising a mixture of:  
(a) a hydrolyzable perfluoropolyether isocyanate ~~derived urethane or urea~~ silane or a mixture thereof comprising the reaction product of:

(i) a fluorinated polyether compound of the formula



wherein  $R_f$  is a monovalent or divalent polyfluoropolyether group; T and T' each independently represents  $-\text{CO}_2\text{R}^3$ , where  $\text{R}^3$  is ~~hydrogen or~~ hydroxyalkyl, or  $-\text{C}(\text{O})\text{N}(\text{R}^1)(\text{R}^2)$ , where  $\text{R}^1$  and  $\text{R}^2$  are independently hydrogen, ~~poly~~hydroxyalkylene, dihydroxyalkylene, or polyalkylenepolyamine with the proviso that both R1 and R2 are not hydrogen at the same time;  $\frac{y}{k}$  is an integer from 0 to 5; k is an integer from 1 to 5; and y is 0 or 1; and

(ii) a silane compound of the formula



wherein  $T''$  is  $-\text{NCO}$ ;  $Q''$  is  $-(\text{C}_n\text{H}_{2n})-$ , where n is 2 to 6; R is an alkyl group of 1-4 carbon atoms; Y is a hydrolyzable group; and x is 0, 1 or 2;

(b) at least one non-fluorinated compound of the formula:



wherein R' is a C<sub>1</sub>-C<sub>4</sub> alkyl group; p is 2, 3 or 4; q is 0, 1 or 2, wherein the sum of p + q is 4, and Y' is a C<sub>1</sub>-C<sub>4</sub> alkoxy group; and

(c) optionally, at least one non-fluorinated compound of the formula:



wherein R'' is a C<sub>6</sub>-C<sub>20</sub> alkyl group and Y'' is a C<sub>1</sub>-C<sub>4</sub> alkoxy group, or a compound of the formula:



wherein L is a reactive functional group selected from an amino, an epoxy, a mercaptan, a methacrylate and an anhydride group; Q'' is -(C<sub>n</sub>H<sub>2n</sub>)-, where n is 2 to 6; Y'' is a C<sub>1</sub>-C<sub>4</sub> alkoxy group.

25. (Withdrawn) A composition comprising a mixture of:

(a) a hydrolyzable perfluoropolyetherisocyanate derived silane or a mixture thereof comprising the reaction product of:

(i) a fluorinated polyether compound of the formula



wherein R<sub>f</sub> is a monovalent or divalent polyfluoropolyether group; T and T' each independently represents -CO<sub>2</sub>R<sup>3</sup>, where R<sup>3</sup> is hydrogen or hydroxyalkyl, or -C(O)N(R<sup>1</sup>)(R<sup>2</sup>), where R<sup>1</sup> and R<sup>2</sup> are independently hydrogen, polyhydroxyalkylene or polyalkylenepolyamine;  $\frac{y}{k}$  is an integer from 0 to 5; k is an integer from 1 to 5; and y is 0 or 1;

(ii) a silane compound of the formula



wherein T''' is ; -OH, -SH, and NHR, where R is hydrogen or a C<sub>1</sub>-C<sub>4</sub> alkyl group; Q'' is -(C<sub>n</sub>H<sub>2n</sub>)-, where n is 2 to 6; R is an alkyl group of 1-4 carbon atoms; Y is a hydrolyzable group; and x is 0, 1 or 2; and

(iii) an aliphatic or aromatic polyisocyanate of the formula:



wherein Q is a polyalkylene or arylene group optionally containing oxygen, nitrogen, or carboxy groups or combinations thereof, and z is an integer of 2 to 5;

(b) at least one non-fluorinated compound of the formula:



wherein R' is a C<sub>1</sub>-C<sub>4</sub> alkyl group; p is 2, 3 or 4; q is 0, 1 or 2, wherein the sum of p + q is 4, and Y' is a C<sub>1</sub>-C<sub>4</sub> alkoxy group; and

(c) optionally, at least one non-fluorinated compound of the formula:



wherein R'' is a C<sub>6</sub>-C<sub>20</sub> alkyl group and Y'' is a C<sub>1</sub>-C<sub>4</sub> alkoxy group, or a compound of the formula:



wherein L is a reactive functional group selected from an amino, an epoxy, a mercaptan, a methacrylate and an anhydride group; Q'' is -(C<sub>n</sub>H<sub>2n</sub>)-, where n is 2 to 6; Y'' is a C<sub>1</sub>-C<sub>4</sub> alkoxy group.

26. (Withdrawn) A composition according to claim 25, further comprising an organic solvent.

27. (Withdrawn) A composition according to claim 26, wherein said organic solvent comprises a solvent capable of dissolving at least 0.01% by weight of component (a).

28. (Withdrawn) A composition according to claim 27, wherein said organic solvent is an alcohol, ketone, ether or ester.

29. (Withdrawn) The composition according to claim 25, wherein said composition is derivable from a partial condensation reaction of components (a), (b) and (c).

30. (Withdrawn) The composition according to claim 25, wherein said composition is derivable from a complete condensation reaction of components (a), (b) and (c).

31. (Withdrawn) A process for preparing a partial or complete condensate comprising reacting components (a), (b) and (c) according to claim 25 in a polar organic solvent in the presence of water and an acid or base catalyst.

32. (Withdrawn) A method of treating a substrate comprising applying to at least part of a surface of said substrate a composition according to claim 25.

33. (Withdrawn) A coated substrate as prepared by the method according to claim 31.